

### **REMARKS**

The substitute specification together with the amended claims place the present U.S. national phase application in better form for examination on the merits.

Also attached hereto is an Abstract of the Disclosure presented on a separate sheet in conformity with the rules of practice.

Based upon the specification and claim amendments to this national phase application, it is believed that the amended specification and amended claims conform with U.S. formal requirements. Additionally, the amended claims as hereinabove presented conform in substance with the corresponding amended claims that were examined in the international application. And based upon the acceptance by the International Preliminary Examining Authority of the invention as it was claimed in the amended claims that were presented in the international application as meeting each of the novelty, the inventive step, and the industrial applicability criteria set forth in the Patent Cooperation Treaty, the claims as amended above are believed to conform with both U.S. formal and U.S. substantive requirements, and they are therefore believed to be in allowable form. Accordingly, an early Notice of Allowance is in order and is respectfully solicited.

Should the examiner have any question after considering this Preliminary Amendment, he is cordially invited to telephone the undersigned

attorney so that any such question can be quickly resolved in order that the present application can proceed toward allowance.

Respectfully submitted,

A handwritten signature in black ink, appearing to read 'Alfred J. Mangels', with a long horizontal flourish extending to the right.

October 3, 2004

Alfred J. Mangels  
Reg. No. 22,605  
4729 Cornell Road  
Cincinnati, Ohio 45241  
Tel.: (513) 469-0470

Attachments: Attachment A  
Attachment B  
Abstract of the Disclosure

**ATTACHMENT B**

**SUBSTITUTE SPECIFICATION**

(Showing All Changes from the Specification in Published International Application No. PCT/SE03/00556, Publication No. WO 03/087016 A1)

**METHOD OF MAKING A HEATING ELEMENT OF MOLYBDENUM SILICIDE TYPE**

**BACKGROUND OF THE INVENTION**

**FIELD OF THE INVENTION**

The present invention relates to a method of manufacturing a heating element of the molybdenum silicide type.

**DESCRIPTION OF THE RELATED ART**

An electric resistance element of the molybdenum silicide type is described in Swedish Patent Specifications 0003512-1 and 0004329-9. According to patent specification 0003512-1 the resistance material of the heating element includes  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  which ~~is caused to contain aluminium~~ contains aluminum to an extent at which the formation of pest is essentially prevented.

It has been found that when such material is operated in a temperature range of 400 – 600 °C no pest, or only a slight amount of pest, is formed. Pest is formed by virtue of the formation of  $\text{MoO}_3$  from  $\text{MoSi}_2$  and  $\text{O}_2$ .

The reason why the formation of pest is significantly reduced or is eliminated is due the formation of  $\text{Al}_2\text{O}_3$ , or a layer rich in  $\text{Al}_2\text{O}_3$ , on the surface of the element

The other Swedish patent specification, 0004329-9, teaches a method of increasing the useful life span of heating elements that essentially consist of molybdenum silicide and alloys of ~~this~~ that basic material when the element operates at high temperatures.

According to ~~this~~ that patent specification, the heating element ~~is caused to contain aluminium~~ contains aluminum to an extent ~~which is~~ sufficient to maintain a stable, slowly growing layer of ~~aluminium~~ aluminum oxide on the surface of the heating element.

According to one preferred embodiment the heating element material ~~is caused to contain~~ contains  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ , where x lies in the range of 0.2 - 0.6.

A material of the molybdenum silicide type that contains ~~aluminium~~ aluminum has been found to possess improved corrosion properties at both low and high temperatures.

Such material is often produced by mixing  $\text{MoSi}_2$  powder with oxidic raw material, such as aluminosilicates. When the raw material is bentonite clay, there is obtained a relatively low melting point ~~which~~ that contributes towards so-called smelt phase sintering, which results in dense materials that ~~contains~~ contain  $\text{MoSi}_2$  and a proportion of ~~aluminium~~ aluminum silicate corresponding to 15 - 20 percent by volume.

Bentonite clay containing chiefly  $\text{SiO}_2$  can be used in the production of heating elements containing  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ . When sintering with an Al-alloyed silicide there takes place a chemical exchange reaction in which the greater affinity of the oxygen to Al than to Si results in Si leaving the ~~aluminium~~ aluminum silicate and entering the silicide as a result of Al leaving the silicide and being ~~sucked~~ taken up by the oxide phase. This exchange reaction also contributes towards improved sintering properties of the composite material. The final material contains  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  that is substantially ~~deplete~~ depleted of Al, where the oxide phase contains  $\text{Al}_2\text{O}_3$  in all essentials.

The standard procedure of manufacture involves mixing molybdenum, silicon, and ~~aluminium~~ aluminum in powder form, and firing the powder mix normally under a shielding gas atmosphere. ~~This~~ That results in a cake of the material  $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$ , where y is larger than x in the above formula as a result of said exchange reaction. The reaction is exothermic. The cake is then crushed and ground down to a fine particle size normally in the order of 1 – 20  $\mu\text{m}$ . ~~This~~ The resulting powder is mixed with bentonite clay ~~such as~~ to form a wet ceramic material. ~~The~~ That material is extruded and dried to a rod form whose diameter corresponds to the diameter of the subsequent heating element. The material is then sintered at a temperature that exceeds the smelting temperature of the bentonite component.

However, there is a drawback with an element of ~~this~~ that kind. The problem is that the oxide that forms on the surface of the element, namely  $\text{Al}_2\text{O}_3$ , sometimes ~~[[,]]~~ peels away or flakes off, i.e., loosens from the surface of the element, in cyclic operation.

A peeling oxide gives poorer protection against continued oxidation of ~~aluminium~~ aluminum, which becomes impoverished in the outer surface of the element more quickly. Moreover, oxide peelings can contaminate the oven in which the element is fitted, with the risk that performance and the appearance of products heat treated in ovens that have such elements will be significantly impaired. This thus restricts the use of such elements in heating processes.

## SUMMARY OF THE INVENTION

This problem is solved by the solution taught in each of the two Swedish Patent Specifications 0201042-9 and 0201043-7, which provide the basis for the claim for priority in the present application.

Swedish Patent Specification 0201042-9 teaches a method of producing a heating element that comprises substantially of molybdenum silicide and alloys of ~~this~~ that basic material. The method is ~~characterised~~ characterized by producing a material that contains chiefly  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  and  $\text{Al}_2\text{O}_3$  by mixing molybdenum aluminosilicide ( $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$ ) with  $\text{SiO}_2$ , where the  $\text{SiO}_2$  is at least 98% pure.

Swedish Patent Specification 0201043-7 teaches the production of a corresponding material, where bentonite clay is used to add silicon dioxide and ~~aluminium~~ aluminum oxide. The bentonite clay ~~shall~~ should have a contaminating substance content of less than 2000 ppm.

It has been found, surprisingly, that there is obtained at low contaminant consistencies an oxide which does not peel after cyclic operation between room temperature and high temperatures, for instance  $1500^\circ\text{C}$ . The present invention is based on the insight that such a pure ~~aluminium~~ aluminum-oxide-building molybdenum silicide material can be produced beneficially by beginning partly with other material and compounds than those given above.

## DESCRIPTION OF THE PREFERRED EMBODIMENTS

The present method of production of a heating element that is comprised essentially of molybdenum silicide and its alloys includes the step of producing a

material that contains essentially  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  and  $\text{Al}_2\text{O}_3$  by mixing a mixture of silicon and molybdenum compound with an ~~aluminium~~ aluminum compound.

According to the invention, silicon and the molybdenum compound include  $\text{Mo}(\text{Si}_{1-y}\text{Al}_y)_2$  and are mixed with either an ~~aluminium~~ aluminum compound consisting of  $\text{Al}_2\text{O}_3$  or of  $\text{Al}(\text{OH})_3$ , and are optionally mixed with one or more of the compounds  $\text{SiO}_2$ ,  $\text{Si}_1$  and  $\text{MoO}_3$ .

According to a second embodiment, silicon and the molybdenum compound contain  $\text{MoO}_3$  and  $\text{Al}_1$  and Si and/or  $\text{SiO}_2$ .

According to the invention the input components together have a degree of purity of at least 98%.

According to a preferred embodiment of the invention the input components have a degree of purity of at least 99%.

The mixture ~~is caused to react~~ reacts exothermically and/or by being sintered so that exchange reactions take place, to form the compounds  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  and  $\text{Al}_2\text{O}_3$ , where x ~~is caused to lie~~ lies in the range of 0.4 - 0.6.

There is obtained by this method ~~an~~ a heating element material that is ~~aluminium~~ aluminum-oxide-building and whose ~~aluminium~~ aluminum oxide layers will not peel or flake [[:]] , which was mentioned as a problem in the beginning of this document.

According to one preferred embodiment x ~~is caused to lie~~ lies in the range of 0.45 - 0.55.

According to one preferred embodiment, the  $\text{SiO}_2$  is included in silicates, where the remaining substances in the silicate have such properties that molybdenum silicide

is unable to alloy with said substance or substances, and also have such properties that the symmetry of the crystal lattice of the molybdenum silicide is retained.

It is possible to substitute molybdenum partly with Re, W, or Nb in the material  $\text{Mo}(\text{Si}_{1-x}\text{Al}_x)_2$  without changing the symmetry of the crystal lattice.

Molybdenum can be replaced with tungsten (W) by in an amount corresponding approximately to one third.

According to one preferred embodiment one or more of the following sintering auxiliaries MgO, CaO,  $\text{SiO}_2$ , and  $\text{Y}_2\text{O}_3$  is/are ~~caused to be~~ added to the mixture.

The present invention thus solves the problem mentioned in the introduction and enables the present element to be used beneficially in ovens without detriment to the material treated in the oven.

The present invention shall not be considered to be limited to the ~~aforedescribed~~ above-described embodiments, since variations can be made within the scope of the accompanying claims.

**CLAIMS**

What is claimed is: